



VISUAL CONTACT OUTSIDE



COLD CUT, CRUSH CUT OR
ULTRASONIC



MANUFACTURED IN THE EU

TECHNICAL PROPERTIES

Fabric Characteristic	Standard	
Composition		85 % PVC + 15 % PES
Weight (g/m²)		632 ± 5 %
Thickness (mm)		0.8 ± 5 %
Openness factor %	Internal method	7 %
Light fastness (grey scale level)	EN ISO 4892-2 (exterior) (grey scale level)	5 4 White
Light fastness	EN ISO 105 B02:2002 (interior) blue scale level)	8 7 white
Tearing resistance (daN)	EN ISO 13937-3:2001	Warp 8.3 Weft: 7.1
Breaking strength (daN/5cm)	EN ISO 13934-1:1999	Warp: 141 Weft: 137
Stretch (%)	EN ISO 13934-1:1999	Warp: 20 % Weft: 20 %
Recycled content		2% Pre-consumer
Antibacterial activity	ASTM 2180-018	Microorganism growth inhibition
Roll size		Width 250 cm, Length 16.5 m
Manufacturing properties	Always store rolls horizontally Welding: Thermo or ultrasonic Manufacturing direction: Blinds can be manufactured 'drop to length' or railroaded. BUT do not place blinds manufactured in different directions in the same area, as this difference will be spotted Manufacture panel blinds only 'drop to length' <div style="text-align: center;"> </div>	
Maintenance	Periodic maintenance: remove dust with vacuum cleaner, dry cloth or compressed air In case of accumulated dirt, it can be cleaned using a sponge or soft brush dipped in soapy water or spray cleaner. In both cases the fabric should be rinsed, leaving the curtain to dry open. Under no circumstances should solvents or abrasives that could damage the fabric coating be used, so care should be taken to avoid paint, varnish or ink stains <div style="text-align: right;"> </div>	

Range of colours 2022

White
Grey
Moka
Sky blue
Yellow



Roller and Panel blinds

All specifications are based on average values and may deviate. The values are given for guidance and are not contractual.
Subject to technical modifications