



PHthalate FREE

REACH COMPLIANT



COLD

COLD-CUT, CRUSH-CUT OR
ULTRASONIC



MANUFACTURED IN THE EU

TECHNICAL PROPERTIES

Fabric Characteristic	Standard	
Composition		85 % PVC + 15 % PES
Weight (g/m ²)	EN 12127	610 ± 5 %
Thickness (mm)		0.80 ± 5 %
Light fastness (grey scale level)	EN ISO 105 B06-2002 (interior)	5/ 5 4/ 5 White
Light fastness (blue scale level)	EN ISO 105 B02:2002 (interior)	8/ 8 7/ 8 white
Tearing resistance (daN)	EN ISO 13937-3:2001	Warp: 13,4 Weft: 13,8
Breaking strength (daN/5cm)	EN ISO 13934-1:1999	Warp: 180 Weft: 147
Stretch (%)	EN ISO 13934-1:1999	Warp: 21 % Weft: 21 %
Recycled content		2% Pre-consumer
Antibacterial activity	ASTM 2180-01 y ASTM G21-09	Microorganism growth inhibition
Roll size		Width 250 cm, Length 16,5 m

Environmental & health properties Phthalate-free

Manufacturing properties
 Always store rolls horizontally
 Welding: Thermo or ultrasonic
 Cold-cut, crush-cut or ultrasonic
 Manufacturing direction: Blinds can be manufactured 'drop to length' or railroaded.
 BUT do not place blinds manufactured in different directions in the same area, as this difference will be spotted ↓ →
 Manufacture panel blinds only 'drop to length' ↓

Maintenance
 Periodic maintenance: remove dust with vacuum cleaner, dry cloth or compressed air
 In case of accumulated dirt, it can be cleaned using a sponge or soft brush dipped in soapy water or spray cleaner. In both cases the fabric should be rinsed, leaving the curtain to dry open
 Under no circumstances should solvents or abrasives that could damage the fabric coating be used, so care should be taken to avoid paint, varnish or ink stains



- Vertical blinds
- Roller blinds
- Panel blinds

All specifications are based on average values and may deviate. The values are given for guidance and are not contractual
 Subject to technical modification