



VISUAL CONTACT OUTSIDE



COLD-CUT, CRUSH-CUT OR ULTRASONIC



REACH COMPLIANT,
MANUFACTURED IN THE EU

TECHNICAL PROPERTIES

Fabric Characteristic	Standard	
Composition		85 % PVC + 15 % PES
Weight (g/m ²)	EN 12127	610 ± 5 %
Yarn/cm	Internal method	Warp: 16 Weft: 13,5
Yarn diameter (mm)	Internal method	0.40
Openness factor (%)		Approximately 5 %
Thickness (mm)		0.78 ± 5 %
Light fastness (grey scale level)	EN ISO 105 B06-2002 (interior) EN ISO 105 B03:1994 (exterior) EN ISO 105 B04:1998 (exterior) EN ISO 4892-2 (exterior)	5/ 5 4/ 5 White
Light fastness (blue scale level)	EN ISO 105 B02:2002 (interior)	7/ 8 white, other colours 8/8
Tearing resistance (daN)	EN ISO 13937-3:2001	Warp: 6.6 Weft: 5.3
Breaking strength (daN/5cm)	EN ISO 13934-1:1999	Warp: 174 Weft:133
Stretch (%)	EN ISO 13934-1:1999	Warp: 22 % Weft: 21 %
Roll size		Width 250 cm, Length 18.5 m
Recycled content		2 % Pre-consumer
Antibacterial activity	ASTM 2180-01 and ASTM G21-09	Microorganism growth inhibition
Environmental & health properties	Phthalate-free, Lead-free of Bisphenol A-free Free of substances on the REACH SVHC list	
Manufacturing properties	Always store rolls horizontally Cold-cut, crush-cut or ultrasonic. Welding: Thermo or ultrasonic Manufacturing direction: ↓ → Blinds can be manufactured 'drop to length' or railroaded. BUT do not place blinds manufactured in different directions in the same area, as this difference will be spotted Manufacture panel blinds only 'drop to length' ↓	
Maintenance	Periodic maintenance: remove dust with vacuum cleaner, dry cloth or compressed air In case of accumulated dirt, it can be cleaned using a sponge or soft brush dipped in soapy water or spray cleaner. In both cases the fabric should be rinsed, leaving the curtain to dry open. Under no circumstances should solvents or abrasives that could damage the fabric coating be used, so care should be taken to avoid paint, varnish or ink stains	



Panel blinds



Vertical blinds



Skylight blinds



Roller blinds

All specifications are based on average values and may deviate. The values are given for guidance and are not contractual.
Subject to technical modifications

